

# Powder Coat Paint Re-coating Suggestions

## For Steel and Galvannealed Steel Products Only



The powder coat paints used on our Steel and Galvannealed product may be re-coated provided the following procedures are followed:

- Abrade the entire paint surface with an abrasive pad. Choose a pad designed not to shred, rust or splinter.
- It is recommended that all parts be cleaned well, before any paint is applied in the field. After abrading the surface, the parts should be wiped with an alcohol-based product which will clean and help reopen the surface for the best adhesion of the topcoat. Be sure to read the product directions prior to use.
- Use a high-quality paint that is suitable for metal. Activar Construction Products Group, Inc. cannot accept liability for the performance of specific brands of paint.

\*NOTE: Field re-coating of products other than Steel and Galvannealed Steel, such as Stainless or Aluminum, is not recommended.



9702 Newton Ave S. Bloomington, MN 55431 | 10 Locations Nationwide

 800-554-6077  952-835-2218  sales@activarcpg.com  www.activarcpg.com

### Powder Coat Paint Re-coating Suggestions

\*For steel and galvannealed steel products only\*